

PANalytical

**Quantification of sample PBWO4-3**

<b>R.M.S.:</b>	0.002
<b>Result status:</b>	
<b>Sum before normalization:</b>	23.1 %
<b>Normalised to:</b>	100.0 %
<b>Sample type:</b>	Loose powder
<b>Correction applied for medium:</b>	No
<b>Correction applied for film:</b>	No
<b>Used Compound list:</b>	OxidesVSL
<b>Results database:</b>	omnhefilm11min
<b>Results database in:</b>	c:\panalytical\superq\userdata

	<b>Compound Name</b>	<b>Conc. (%)</b>
1	Al2O3	0.201
2	B2O3	! 0.000
3	F	! 0.000
4	Fe2O3	0.658
5	Li2O	! 0.000
6	NiO	0.175
7	PbO	45.113
8	SiO2	0.150
9	WO3	53.506
10	ZnO	0.090
11	ZrO2	0.106

*MW* 8-10-16